



# PROTHERM LIGHT® FRP

**COUPLED BOARD  
FOR FIRE PROTECTION**

PROTHERM LIGHT® FRP Coupled board for fire protection			
PRODUCT	Coupled board for the fire protection of structural reinforcement in FRP and organic resin.		
PACKAGING AND STORAGE	<ul style="list-style-type: none"> <li>Board with smooth edge 360 x 700 mm [0,252 m<sup>2</sup>].</li> <li>Pallet: 80 x 120 cm, height 110 cm - Content: 15 boxes - Each box contains 5 boards.</li> <li>Available colours: white/grey.</li> <li>Stock in a dry and fresh place, away from frost and water.</li> </ul>		
COMPOSITION	Composite board composed of a nanotechnological panel and a layer of thermal insulating plaster, total thickness 40 mm.		
APPLICATION FIELDS	Passive fire protection of structural reinforcement in FRP and organic resin.		
WARNINGS	<ul style="list-style-type: none"> <li>Do not apply under the rain, with temperatures below +5 °C and risk of frost.</li> <li>Apply the product with relative humidity between 45% and 80%. Do not apply with too low relative humidity.</li> <li>For application details, consult the "Application manual Protherm Light® FRP" or contact the Edilteco Technical Department.</li> </ul>		
TECHNICAL CHARACTERISTICS <i>(Thermal insulating panel)</i>	DESCRIPTION	UNIT OF MEASURE	VALUE
	Fire reaction:	-	A2-s1,d0
	Nominal density:	kg/m <sup>3</sup>	200 ± 30
	Specific heat:	J/kgK	1.000
	Permeability to water vapour:	μ	0,07
TECHNICAL CHARACTERISTICS <i>(Thermal insulating plaster)</i>	DESCRIPTION	UNIT OF MEASURE	VALUE
	Specific weight:	kg/m <sup>3</sup>	300
	Resistance to water vapour diffusion:	μ	9
	Fire reaction:	-	A1
TECHNICAL CHARACTERISTICS OF THE COUPLED BOARD	DESCRIPTION	UNIT OF MEASURE	VALUE
	Heat resistance:	m <sup>2</sup> K/W	2,8
	Board density:	kg/m <sup>2</sup>	11
	Thickness:	mm	40
	Height:	mm	700
	Width:	mm	360
Weight:	kg	≈ 3	
<p>All the indications provided in this technical data sheet are purely approximate and not binding for legal purpose. The data listed has been gathered from laboratory tests and it hence follows that in practical applications on building sites the final characteristics of the products may be subject to substantial variations depending on the meteorological conditions and the installation. The user must always check suitability of the product for its specific use, undertaking all liability implicit in and deriving from use of the product, as well as comply with all methods and instructions for use generally referable to "workmanlike" execution. Edilteco S.p.A. reserves the right to change the contents of this mechanical data sheet on its final judgements. The spreading of this data sheet through any media, supersedes and cancels the validity of any other technical data sheet previously published.</p>			



DS PROTHERM LIGHT® FRP . Rev 01/2025 . GB

Edilteco S.p.A. Via dell'Industria, 710 . 41038 San Felice sul Panaro (MO) Italy . Ph. +39 0535 82161 . Fax +39 0535 82970  
www.edilteco.com | info@edilteco.com

COMPANY WITH  
QUALITY SYSTEM  
CERTIFIED BY DNV  
ISO 9001