



ISOLTECO® 150

PRE-MIXED PLASTER,
WITH HIGH THERMAL INSULATION CAPACITY

ISOLTECO® 150

Pre-mixed plaster, with high thermal insulation capacity

PRODUCT	Pre-mixed plaster based on pre-dosed selected hydraulic binders, virgin expanded polystyrene beads perfectly spherical with consistent grain size, enriched with a special E.I.A. additive and special additives.			
PACKAGING AND STORAGE	<ul style="list-style-type: none"> · Bag of 60 L yield. · Pallet of 44 bags. · It is recommended the use within 6 months from the packaging. The product maintains the technical characteristics for over 12 months if conveniently stored (in a dry and fresh place, protected from frozen, water and direct sunlight). It is recommended to use suitable protection devices. 			
FIELDS OF APPLICATION	<ul style="list-style-type: none"> · Thermal insulation of external walls. · Thermal insulation of internal walls. · Thermal insulation of ceilings. · Elimination of thermal bridges. · Protection of the walls from rain. 			
PREROGATIVES	<ul style="list-style-type: none"> · For internal and external use (once applied and "cured" does not have problems in case of rain, moisture and low / high temperatures). · The surface can be left rough or be finished with smoothing or finishing mortars. · It strongly speeds up the application time of the final smoothing. · It guarantees a high thermal insulation. 			
CONSUMPTION / YIELD	THICKNESS AND YIELD		THICKNESS AND YIELD	
	2 cm	3,00 m ²	7 cm	0,86 m ²
	3 cm	2,00 m ²	8 cm	0,75 m ²
	4 cm	1,50 m ²	10 cm	0,60 m ²
	5 cm	1,20 m ²	12 cm	0,50 m ²
6 cm	1,00 m ²	-	-	
SUPPORT PREPARATION *	<ul style="list-style-type: none"> · The substrate must be clean, sufficiently solid, absorbent, and free of loose parts, dust, and residues of insulating materials. · Before applying Isolteco® 150, moisten the substrate using methods suitable for the type of substrate. · For low-absorption substrates, apply an adhesion promoter, such as Edilstik, over the entire surface and then apply Isolteco® 150 on the treated surface while still wet ("wet-on-wet"). · For substrates with very low absorption or high absorption, apply a scratch coat made of cement slurry and sand mixed with Edilstik, or use a ready-to-use scratch coat product before proceeding with the application of Isolteco® 150. · Intermediate leveling strips must be created exclusively using Isolteco® 150. Alternatively, wooden battens or chamfered metal strips can be used, provided that after applying Isolteco® 150, these are removed, and the resulting voids are filled and leveled with Isolteco® 150. The leveling strips should be no more than 2 m apart. · Edges and openings (doors, windows, etc.) should be prepared with the installation of appropriate metal corner protectors, secured with cement-based markers or thermal mortar. Additionally, edges can be created during the application of Isolteco® 150 using wooden boards. However, this method results in less impact-resistant finished edges. 			

APPLICATION *	<p>Application using a plastering machine (recommended): it is essential to equip the plastering machine with a turbo or mini-turbo, with a helical mixer featuring a solid helix, a specific tank for lightweight products, a long-pitch screw with a pin, and a cap or nozzle \varnothing 14 mm.</p> <p>Manual application: mix using a concrete mixer or horizontal mixer, hydrating the contents of one bag with approximately 5 - 6 liters of clean water. Mix for at least 5 minutes and no more than 10 minutes.</p> <p>Installation:</p> <ul style="list-style-type: none"> Apply an initial layer of approx. 1 cm of Isolteco® 150. Once the first layer has set (no less than 4 hours, no more than 24 hours), apply the second layer (maximum 2.5 - 3 cm). If additional layers are required, repeat the same procedure. Total permitted thickness: minimum 2 cm - maximum 20 cm. After 24 - 96 hours from the application of Isolteco® 150 (depending on environmental conditions and applied thickness), proceed with surface scraping using a float or straight edge. Wait at least 7 days after applying Isolteco® 150, and once it has dried based on the applied thickness, proceed with the application of a skim coat using Ecap® ADP. To increase resistance to concentrated impacts, embed a fiberglass mesh (160 gr/m²) in the skim coat. The application thickness of the skim coat must be 4 - 5 mm. <p>Finishes for painting: after curing the base plaster, apply Ecap® ADP. Once matured, apply breathable paint such as Ecap® STP Silicate Paint or Ecap® SP Silicone Paint, after treating the surface with Ecap® F primer. Lime-based breathable paints are also compatible.</p> <p>Colored finishes: it can receive breathable colored finishes, such as Ecap® SC Silicone Colour or Ecap® STC Silicate Colour, applied directly to the base plaster after treating it with Ecap® F primer.</p>		
WARNINGS	<ul style="list-style-type: none"> Do not apply under direct sunlight or at temperatures above +35 °C. If plastering is carried out under direct sunlight, appropriate precautions must be taken (e.g., scaffolding nets). Do not apply under rain, at temperatures below +5 °C, or when there is a risk of frost. In any case, never add antifreeze products. Apply at a relative humidity between 45% and 80%. Do not apply when the relative humidity is too low. For detailed application and execution instructions, consult the relevant "Installation Manual - Isolteco®" or contact the <i>Edilteco Technical Office</i>. 		
TECHNICAL CHARACTERISTICS	Dry density:	150 kg/m ³	-
	Specific weight (dry mortar):	approx. 165 kg/m ³	UNI EN 1015-10
	Fire reaction class:	A2-s1,d0	EN 13501-1
	Adherence:	0,1 N/mm ²	UNI EN 1015-12
	Water absorption by capillarity:	0,1 kg/m ² s ^{0,5} W1	UNI EN 1015-18 UNI EN 998-1
	Water vapor diffusion resistance μ :	9	UNI EN 1015-19
	Thermal conductivity λ_D :	0,058 W/mK	UNI EN 12667
	Compressive strength:	1,16 N/mm ²	UNI 6132
	Flexural strength:	0,42 N/mm ²	UNI 6133
	Specific heat kJ/kgK:	1,0	UNI EN 1745
	Durability (frost / thaw):	valued	UNI EN 998-1
<p>All the indications provided in this technical data sheet are purely approximate and not binding for legal purpose. The data listed has been gathered from laboratory tests and it hence follows that in practical applications on building sites the final characteristics of the products may be subject to substantial variations depending on the meteorological conditions and the installation. The user must always check suitability of the product for its specific use, undertaking all liability implicit in and deriving from use of the product, as well as comply with all methods and instructions for use generally referable to "workmanlike" execution. Edilteco S.p.A. reserves the right to change the contents of this mechanical data sheet on its final judgements. The spreading of this data sheet through any media, supersedes and cancels the validity of any other technical data sheet previously published.</p>			

* For more detailed information consult the "Isolteco® - Application Manual" or contact *Edilteco Technical Department*.

LEED CRITERIA		
SECTIONS	CREDITS	TECHNICAL DESCRIPTIONS
Energy and Atmosphere (EA)	Prerequisite 2	Minimum energetic performances
	Credit 1	Optimization of the energy performances
Materials and Resources (MR)	Credit 5	Extracted, processed and produced at a limited distance materials (regional materials)

