



$\lambda_0 =$
0,065
W/mK

ISOLCAP 250

PRE-MIXED UNDERLAY, LIGHTWEIGHT AND THERMAL INSULATING

ISOLCAP 250 Pre-mixed underlay, lightweight and thermal insulating	
COMPOSITION	Selected hydraulic binders pre-dosed at 250 kg/m ³ , virgin expanded polystyrene beads perfectly spherical with high thermal insulation capacity (Ø 3 - 6 mm), enriched with a special E.I.A. product that ensures perfect mixing, optimal pumpability, and homogeneous distribution of the beads in the mixture, along with special additives.
PACKAGING AND STORAGE	<ul style="list-style-type: none"> · Bags of 70 L yield. · Pallets of 44 bags. · It is recommended the use within 6 months from the packaging. The product maintains the technical characteristics for over 12 months if conveniently stored (in a dry and fresh place, protected from frost, water and direct sunlight). It is recommended to use suitable protection devices.
FIELDS OF APPLICATION	<ul style="list-style-type: none"> · Lightweight thermal insulating base screeds (with or without falls). · Lightening and filling castings. · Thermal insulation of roofing (pitched or flat roofs with or without falls). Suitable for direct laying of pre-fabricated waterproofing membranes (hot bituminous, cold bituminous, cold synthetic) or solvent-free liquid sheaths.
CONSUMPTION / YIELD	1 m ³ of lightweight thermal insulating mortar is obtained with 13 - 14 bags (depending on the equipment used and the accuracy of the mix).
SURFACE PREPARATION	<ul style="list-style-type: none"> · Thoroughly clean the laying surface removing residues and dust. · Prepare the level points. · Moisten the laying surface (if absorbent) taking care not to create puddles. · Highly absorbent surfaces (such as hollow brick, etc.): proceed to the perfect cleaning and dusting removal from the laying surface. Apply an adhesion promoter grout and an absorbing reductor composed of cement / Edilstik / clean water (Edilstik / water ratio 1:1). After drying, wet the laying surface and proceed to lay the lightweight screed. Wet the surface as you proceed with the application of the lightweight screed. · Non-absorbent surfaces: before applying Isolcap 250, treat the surface with Edilkronos Universal.
APPLICATION	<p>It can be mixed with:</p> <ul style="list-style-type: none"> · Drill with whisk. · Cement mixer. · Mixer type "Turbomalt". <p>It can be mixed and pumped on site with:</p> <ul style="list-style-type: none"> · Politerm® Machine (see Edilteco equipment). · Isolcap Machine (see Edilteco equipment). · Truck mixer and concrete pump. · Pump type "Turbosol". <p>Hydrate with clean water in proportion of 6 - 8 L per bag. Mix for at least 5 minutes and not more than 10 minutes.</p>
WARNINGS	<ul style="list-style-type: none"> · Do not apply with temperatures under +5 °C or over +35 °C or under the direct sunlight. If the application is made under the direct sunlight, necessary precautions must be taken (e.g. mesh or similar that cover the scaffolding). · It is recommended to lay edge strips of acoustic insulation higher than the floor covering. · Minimum thickness: <ol style="list-style-type: none"> a) Absorbent substrates: 5 cm. For reduced thicknesses, refer to the "Isolcap Installation Manual" or contact the Edilteco Technical Office. b) Non-absorbent surface: consult "Isolcap Installation Manual" or contact the Edilteco Technical Department. · For detailed application methods consult "Isolcap Installation Manual". · During the change of each pallet, verify the quantity of water into the mixture.



Edilteco S.p.A. Via dell'Industria, 710 . 41038 San Felice sul Panaro (MO) Italy . Ph. +39 0535 82161 . Fax +39 0535 82970
www.edilteco.com | info@edilteco.com

COMPANY WITH
QUALITY SYSTEM
CERTIFIED BY DNV
ISO 9001

TECHNICAL CHARACTERISTICS	Dry density:	250 kg/m ³	-
	Specific weight (dry mortar):	approx. 265 kg/m ³	-
	Thermal conductivity λ_0 :	0,065 W/mK	UNI EN 12667
	Compressive strength:	0,83 N/mm ²	UNI 6132
	Flexural strength:	0,46 N/mm ²	UNI EN 13892-2
	Permeability to water vapour μ :	6,9	UNI EN ISO 12572
	Specific heat kJ/kgK:	1,0	UNI EN 1745
	Acoustic performance ΔL_w :	14 dB *	UNI EN 12354-2
	Moisture resistance:	rotproof	-
	Residual humidity after 28 days:	< 2% by volume (5 cm thick, absorbent surface)	-
	Fire reaction class:	A2-s1,d0	EN 13501-1

All the indications provided in this technical data sheet are purely approximate and not binding for legal purpose. The data listed has been gathered from laboratory tests and it hence follows that in practical applications on building sites the final characteristics of the products may be subject to substantial variations depending on the meteorological conditions and the installation. The user must always check suitability of the product for its specific use, undertaking all liability implicit in and deriving from use of the product, as well as comply with all methods and instructions for use generally referable to "workmanlike" execution. Edilteco S.p.A. reserves the right to change the contents of this mechanical data sheet on its final judgements. The spreading of this data sheet through any media, supersedes and cancels the validity of any other technical data sheet previously published.

* Value obtained in laboratory with 5 cm of Isolcap 250 + 5 cm of screed.

	SECTION	CREDITS	TECHNICAL DESCRIPTION
LEED CRITERIA	Energy and Atmosphere (EA)	Prerequisite 2	Minimum energetic performances
		Credit 1	Optimization of the energetic performances
	Material and Resources (MR)	Credit 5	Extracted materials, processed and produced at a limited distance